

Naturaltech Pty Ltd (WoodEvo™ Home Advanced Deck)

TEST REPORT

SCOPE OF WORK

WoodEvo Composite Deck

REPORT NUMBER

210818011SHF-001

TEST DATE(S)

2021-08-19 - 2021-09-07

ISSUE DATE

2021-09-07

PAGES


6

DOCUMENT CONTROL NUMBER

LFT-APAC-SHF-OP-10k(May 1, 2021)

© 2021 INTERTEK

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch



Test Report

Statement

- 1.This report is invalid without company's special seal for testing on assigned page.
- 2.This report is invalid without authorized person's signature.
- 3.This report is invalid where any unauthorized modification indicated.
- 4.Don't copy this report in partial (except full copy) without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.
- 5.Any holder of this document is advised that this report is for the exclusive use of Intertek's Customer and is provided pursuant to the agreement between Intertek and its Customer. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report was made with due care within the limitation of a defined scope of work and on the basis of information, materials and instructions received from the Customer or its nominated third parties. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. The tests results are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results.
- 6.Intertek's written consent is required to use Intertek's name or logo on the object, product or service being tested. The observations and test results in this report relate only to the sample under test. This report alone does not indicate that the item, product or service has passed any Intertek certification program.
- 7.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.



Test Report

Issue Date: 2021-09-07 Intertek Report No. 210818011SHF-001
 Applicant: Naturaltech Pty Ltd (WoodEvo™ Home Advanced Deck)
 Address: 5/21 Howleys Road, Notting Hill VIC 3168
 Attn: Owen
 Test Type : Performance test, samples provided by the applicant.

Product Information

Product Name	WoodEvo Composite Deck	Brand	WoodEvo
Sample Description	Good Condition	Sample Amount	5 pcs
		Received Date	2021-08-13
Sample ID	Model	Specification	
S210818011SHF.001	Home Advanced	200mm x 32mm x 1000mm	

Test Methods And Standards

Test Standard	AS 4586-2013 Appendix A, Appendix D
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report relates specifically to the sample(s) that were drawn and provided by the applicant or their nominated third party. The reported result(s) provide no warranty or verification on the sample(s) representing any specific goods and/or shipment and only relate to the sample(s) as received and tested.

Report Authorized

 Name: Daniel Zhang Title: Approver	 Name: Flora Fan Title: Reviewer	 Name: Mae Zhang Title: Project Engineer
---	--	--

Test Report

Issue Date: 2021-09-07

Intertek Report No. 210818011SHF-001

Test Items, Method and Results:

Test Item: Wet Pendulum Test
 Test Method: AS 4586-2013 Appendix A
 Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for 48 hours
 Test Temperature: 23 °C
 Slider: Slider 55
 Test Surface: Wet condition
 Test direction: 0°= parallel to length direction
 45°= angle of 45° with length direction or width direction
 90°= parallel to width direction

Test Item	Test Method	Test Result		Class
		Direction	Pendulum SRV	
Wet pendulum test	AS 4586-2013 Appendix A	0°	90	P5
		45°	94	
		90°	90	

Note:

1. Class based on the lowest result of three directions.
2. Test surface and directions were included in Appendix A of this report.

AS 4586 Wet Pendulum Test Classification of Pedestrian Surface Materials

Class	Pendulum SRV	
	Slider 96	Slider 55
P5	>54	>44
P4	45-54	40-44
P3	35-44	35-39
P2	25-34	20-34
P1	12-24	<20
P0	<12	/



Test Report

Issue Date: 2021-09-07

Intertek Report No. 210818011SHF-001

Test Items, Method and Results:

Test Item: Oil-wet inclining platform test

Test Method: AS 4586-2013 Appendix D

Conditioning: Condition the test specimens at $(23 \pm 2)^{\circ}\text{C}$ and $(50 \pm 5)\%$ relative humidity for 48 hours

Test Item	Test Method	Test Result
Oil-wet inclining platform test	AS 4586-2013 Appendix D	Angle: 37.4° Classification: R13

Note:

1. Test item was subcontracted on accreditation by CNAS L1401.

Classification of Pedestrian surface materials according to the oil-wet inclining platform test

Classification	Angle, degrees
No Classification	$X < 6$
R9	$6 \leq X < 10$
R10	$10 \leq X < 19$
R11	$19 \leq X < 27$
R12	$27 \leq X < 35$
R13	$X \geq 35$




Test Report

Issue Date: 2021-09-07

Intertek Report No. 210818011SHF-001

Appendix A: Sample Received Photo



Test surface



Back view



Section view

Revision:

NO.	Date	Changes
210818011SHF-001	2021-09-07	First issue

